

## 2/0.2 ACP. Technical Data Sheet

### Panel Dimensions

Panel Thickness	2.0 mm
Aluminium Thickness	0.2 mm
Standard Sizes	1220 mm x 2440 mm 1500 mm x 3050 mm

### Dimensional Tolerances

Thickness	- 0 + 0.2 mm
Width	± 2.0 mm
Length	± 3.0 mm
Diagonal	± 5.0 mm
Thermal Expansion	2.4mm/m @100°C Temp Difference
Aluminium Thickness (mm)	Where applicable as specified in EN485-4; otherwise ± 0.02

### Surface Properties

Paint Thickness (micron)	20
Pencil Hardness	>HB
Toughness of Coating	3T
Temperature Resistance	-50°C to +80°C
Impact Strength (kg/cm <sup>2</sup> )	42
Boiling Water Resistance	Boiling for 2hrs without change
Acid Resistance	Immerse Surface in 2% HC1 for 24Hrs without change
Alkali Resistance	Immersed surface in 2% NaOH for 24Hrs without change
Oil Resistance	Immerse Surface in 20# engine oil for 24hrs without change
Solvent Resistance	Cleaned 100 times with Dimethylbenzene without change
Cleaning Resistance	>1000 times without change
Peel Strength 180	>5 Newton / mm

### Product Properties

Weight	2.59 kg/m <sup>2</sup> *
Water Absorbtion % By Volume	0.01
Thermal Performance R Values	0.0057
Core Composition	Polyethylene

\* Minimum weight is indicated. Weight may vary.

Manufacturer reserves the right to change product specification without prior notice.